



Product Description

BLAZELOK™ IB4 is a water-based, fire protection, intumescent ignition barrier. Five dry mils of **BLAZELOK™ IB4** applied over **SEALECTION® 500** or **SEALECTION Agribalance®** successfully complies with the ICC-ES, AC377, Appendix X as an ignition barrier for use in attics and crawl spaces.

ASTM E84 Flame Spread Smoke Developed	0 20
Protective Properties (as per NFPA 286)	Complies with the AC377, Appendix X as an ignition barrier over SEALECTION 500® and Agribalance® spray polyurethane foams
Flash Point	None
Volatility/VOC	2.7 g/l – significantly below and complies with 50 g/l AQMD & EPA
Solvents	Water Based
Toxicity	Non-Toxic & No Formaldehyde
Environmental Impact (as per greenguide.com)	EPA & SCAQMD & LEED compliant
Weight per Gallon	10.3 – 10.7 lb.
Solids by Volume	51-54%
Color	Dull Flat White
Wet film / coat to DFT	9 mils dries to 5 mils, nominal.
Recommended final DFT	5 mil to comply with AC377, Appendix X
Dry Times	2-3 hrs. depending on humidity/temperature. Humidity above 50% RH has a significant impact on drying time.
Recommended Equipment	Graco® 695/ASM2100 3300 psi with spray gun tip model number RAC 521 or LTX 521 or larger. Hose size: use ¼" dia. last 50' to gun, additional lengths of hose use minimum 3/8" dia. to minimize pressure loss. Remove pump and gun filters prior to spraying.
Coverage	Up to 175 ft ² /gallon at 5 mils dry on a relatively smooth surface. Coverage rates will be reduced on foam surfaces with large undulations or rough surfaces.
Minimum temperatures	Product pail temperature, 70°F Substrate temperature, 50°F Use infrared gun to confirm temperatures.
Fungus/Mold Resistance	No mold growth per ASTM D 3273 test

Please contact your DEMILEC (USA) Technical Services Representative for assistance regarding the installation of this product.



Disclaimer: The information herein is to assist customers in determining whether our product is suitable for their application(s). We request that customers inspect and test our product before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent inferred. All patent rights are reserved.

